

|                   |  |
|-------------------|--|
| Basis             | <b>Universal general purpose resin</b> |
| Resin             | <b>AH 100</b>                          |
| Hardener          | <b>TGL</b>                             |
| Colour            | yellow transparent                     |
| Further hardeners | <b>D / GL / TGS / TG / SR</b>          |

## Applications

- Laminating resin for fabrics
- Bonding resin for fillers

## Properties

- unfilled
- slow curing
- for large volume back fillings

## Processing data

| Product               |                                 | Mixture<br>AH 100 / TGL | Resin<br>AH 100    | Hardener<br>TGL    |
|-----------------------|---------------------------------|-------------------------|--------------------|--------------------|
| Colour                |                                 | yellow transparent      | yellow transparent | yellow transparent |
| <b>Mixing ratio</b>   | <b>p. b. w.</b>                 |                         | <b>100</b>         | <b>20</b>          |
| Viscosity at 25°C     | mPas                            | 550 ± 100               | 900 ± 150          | 100 ± 20           |
| Density at 20°C       | g / cm <sup>3</sup>             | 1,12 ± 0,02             | 1,15 ± 0,02        | 0,96 ± 0,01        |
| Pot life 200 g / 20°C | min.                            | 65 - 75                 | -                  | -                  |
| Curing time at RT     | hrs.                            | 18 - 20                 | -                  | -                  |
| Post curing           | Time in h/<br>Temperature in °C | -                       | -                  | -                  |

## Physical data

| Properties                    | Inspect. requirem. | Unit              | Value      |
|-------------------------------|--------------------|-------------------|------------|
| Flexural strength             | EN ISO 178         | MPa               | 105 ± 5    |
| Flexural modulus              | EN ISO 178         | MPa               | 3000 ± 200 |
| Flexural strength at breakage | EN ISO 178         | %                 | 4,7 ± 0,5  |
| Compressive strength          | EN ISO 604         | MPa               | 100 ± 8    |
| Impact resistance (Charpy)    | EN ISO 179         | kJ/m <sup>2</sup> | 37 ± 10    |
| Heat resistance (HDT)         | DIN EN ISO 75 B    | °C                | 76 ± 2     |
| Shore hardness                | DIN 53505          | Shore D           | 87 ± 3     |

## Sales units (packages)

|       |                   |               |  |
|-------|-------------------|---------------|--|
| Units | Resin<br>hardener | AH 100<br>TGL | 5,000 kg / 10,000 kg / 25,000 kg / 50,000 kg / 220,000 kg<br>1,000 kg / 1,500 kg / 2,000 Kg / 2,500 kg / 5,000 kg / 25,000 kg<br>/ 50,000 kg |
|-------|-------------------|---------------|--|

## Processing instructions

The temperature of material and processing should be between 18 and 25° C.  
The mixing of resin and hardener should be made intensively and if possible without any bubbles at room temperature.

## In General

**ebalta** AH 100 is a very thin, unfilled epoxy resin, which can be used with different hardeners. Depending on the application the suitable hardener can be mixed with the resin AH 100.

AH 100 / TGL is preferentially used for big volume backfillings.

## Storing

At appropriate storage (18-25°C) in closed original container 12 months. Occuring crystallization due to disadvantageous storage conditions can be made return by warming up the material at approx. 60° C.

Already opened containers should be closed immediately after use and be protected against moisture. This material should be used as soon as possible.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany  
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . info@ebalta.de . www.ebalta.de