

| | |
|-----------------|----------------------------------|
| Basis | Flexible PU casting resin |
| Resin | GM 951 Comp. A |
| Hardener | GM 951 Comp. B |
| Colour | black |
| Further colours | beige |

Applications

- Casting mould for gypsum
- Casting mould for plastic
- Casting mould for wax
- Casting mould for ceramic materials
- Casting mould for PU-foam
- Casting mould for cement
- Gaskets
- Sealing profiles in core boxes
- Jigs

Properties

- shore A hardness about 50
- high tear strength
- well castable

Processing data

| Product | | Mixture GM 951 / Comp. A+B | Resin GM 951 Comp. A | Hardener GM 951 Comp. B |
|-----------------------|---------------------|-------------------------------|-------------------------|----------------------------|
| Colour | | black | black | transparent |
| Mixing ratio | p. b. w. | | 100 | 10 |
| Viscosity at 25°C | mPas | 5000 ± 500 | 6500 ± 1000 | 40 ± 10 |
| Density at 20°C | g / cm ³ | 1,25 ± 0,03 | 1,29 ± 0,03 | 0,962 ± 0,03 |
| Pot life 200 g / 20°C | min. | 25 - 30 | - | - |
| Curing time at RT | hrs. | 2 - 5 | - | - |

Physical data

| Properties | Inspect. requirem. | Unit | Value |
|------------------------------------|--------------------|----------------------------------|-----------|
| Flexural strength | EN ISO 178 | MPa | - |
| Flexural modulus | EN ISO 178 | MPa | - |
| Flexural strength at breakage | EN ISO 178 | % | - |
| Tensile strength | EN ISO 527 | MPa | 2,0 ± 0,5 |
| Elongation | EN ISO 527 | % | 600 ± 50 |
| Compressive strength | EN ISO 604 | MPa | - |
| Impact resistance (Charpy) | EN ISO 179 | kJ/m ² | - |
| Heat resistance (Martens) | DIN 53458 | °C | - |
| TG in TMA T _g | Methode TMA | °C | n. a. |
| Shore hardness | DIN 53505 | Shore A | 47 ± 3 |
| Coefficient of linear expansion | DIN 53752 | 10 ⁻⁶ K ⁻¹ | - |
| Linear shrinkage | internal | % | - |
| Tear resistance / angle test piece | EN ISO 34-1 | kN/m | 10 ± 0,5 |

Sales units (packages)

| | | | |
|--------------|----------|--------------------|---|
| Packing size | B-Pack | GM 951 / Comp. A+B | Resin 10 x 0,800 kg + Hardener 10 x 0,080 kg = 8,800 kg |
| Units | Resin | GM 951 Comp. A | 15,000 kg |
| | Hardener | GM 951 Comp. B | 1,500 kg |

Processing instructions

Material- and working- temperature: between 18 - 25 °C.

Close containers after use.

Seal porous mould surfaces first (**ebalta** mould sealer).

For optimum mould releasing we recommend a special release agent (like T1-1), which can be applied easily with a brush or be sprayed. Releasing of the mould 2-3 times, evaporate for about 20 min. after each releasing.

Mixing ratio resin/hardener according to instructions.

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent

Both components can be easily mixed free from air bubbles in small quantities by hand with a round stirring rod or in larger quantities with a spiral stirrer.

In General

The product is a very soft elastic polyurethane casting compound.

ebalta GM 951 is suitable as a flexible casting system in the field of mould- and tooling for parts which require low shore hardness and high tear propagation resistance due to deep under cuts. Mould temperatures of about 60 °C lead to faster curing and therefore short demoulding time.

Reactive casting resins must not be cast into elastic casting compound moulds, before complete curing of GM 951 (2-3 days).

For individual formulation of the shore hardness, GM 900 can be mixed with GM 951 (see mixing table).

Parts/moulds must not be cast with addition curing silicone, since this might lead to faulty reactions when curing the silicone.

With the A-component GM 951 This a spreadable surface resin can be obtained.

Storing

Storage at room temperature (18 – 25°C) in closed original container 6 months.

Already opened containers should be closed immediately after use and should be used as soon as possible.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices!

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . info@ebalta.de . www.ebalta.de