

Basis	<b>2 - Component - Epoxy Resin</b>
Resin	<b>LH 27 resin</b>
Hardener	<b>LH 27 hardener</b>
Colour	transparent

### Applications

- Boatbuilding
- Mould constructions
- Vacuum infusion
- Injection process

### Properties

- high temperature resistance
- low viscosity
- excellent wet-out characteristics
- heat curing

### Processing data

Product		Mixture LH 27 / resin + hardener	Resin LH 27 resin	Hardener LH 27 hardener
Colour		transparent	transparent	transparent
<b>Mixing ratio</b>	<b>p. b. w.</b>		<b>100</b>	<b>32</b>
Viscosity at 25°C	mPas	500 ± 50	2200 ± 400	80 ± 10
Density at 20°C	g / cm <sup>3</sup>	1,10 ± 0,02	1,17 ± 0,02	0,96 ± 0,02
Pot life 100 g / 20°C	min.	210 - 270	-	-
Pot life 500 g / 23°C	min.	-	-	-
Curing time at RT	hrs.	-	-	-
Post curing	Time in h/ Temperature in °C	2 / 75 4 / 160 (unbedingt einhalten)	-	-

### Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	135 ± 5
Flexural modulus	EN ISO 178	MPa	2950 ± 250
Flexural strength at breakage	EN ISO 178	%	8 ± 1
Tensile strength	EN ISO 527	MPa	70 ± 5
Compressive strength	EN ISO 604	MPa	80 ± 5
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	26 ± 5
Heat resistance (Martens)	DIN 53458	°C	117 ± 3
Glass transition temperature TG	TMA	°C	> 150
Shore hardness	DIN 53505	Shore D	87 ± 3

### Sales units (packages)

Units	LH 27 resin	can 25 kg / barrel 50 kg / barrel 225 kg / container 1000 kg
	LH 27 hardener	can 8 kg / can 24 kg / barrel 180 kg

## Processing instructions

The material- and processing temperature should be between 18°C – 25°C. The resin and hardener should be mixed intensively and bubble-free at room temperature.

For parts which don't require GL-approval, the pot life of the system can be accelerated by mixing the hardener BIV 800 with hardener W 15.

The mixing ratio resin-hardener remains 100 : 30. Pot life table for the mixture with different hardeners on demand.

Before demoulding the part on the mould has to be post cured for some hours at 50 - 60°C to avoid cold brittleness.

## Storing

At appropriate storage (room temperature) in closed original container 9 months.

Occurring crystallization, due to disadvantageous storage conditions, can be made return by warming up the material at approx. 60 °C.

Already opened containers should be closed immediately after use and also protected against moisture. Material should be used as soon as possible.

## Safety measure

When processing this product the recommended protection measures of the government safety organization of the chemical industry should be followed. Safety advices should be followed.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany  
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . info@**ebalta**.de . www.**ebalta**.de