

Basis	<b>Medium fast casting resin system with high impact strength</b>
Resin	<b>SG 131 Comp. A</b>
Hardener	<b>PUR 11 Comp. B</b>
Colour	white

## Applications

- Foundry patterns
- Core boxes
- Pattern plates
- Negatives
- Prototypes
- Coping models
- Jigs
- Mould probes for trimming of prototypes

## Properties

- unfilled
- long processing time
- high impact strength

## Processing data

Product		Mixture SG 131 / PUR 11	Resin SG 131 Comp. A	Hardener PUR 11 Comp. B
Colour		white	white	yellow
<b>Mixing ratio</b>	<b>p. b. w.</b>		<b>100</b>	<b>100</b>
Viscosity at 25°C	mPas	200 ± 80	400 ± 100	25 ± 10
Density at 20°C	g / cm <sup>3</sup>	1,06 ± 0,02	1,01 ± 0,02	1,10 ± 0,02
Pot life 200 g / 20°C	min.	9 - 15	-	-
Curing time at RT	hrs.	5 - 8	-	-

## Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	38 ± 5
Flexural modulus	EN ISO 178	MPa	1025 ± 150
Flexural strength at breakage	EN ISO 178	%	7,6 ± 0,3
Compressive strength	EN ISO 604	MPa	32 ± 5
Impact resistance (Charpy)	EN ISO 179	kJ/m <sup>2</sup>	30 ± 5
Heat resistance (HDT)	DIN EN ISO 75 B	°C	69 ± 2
Shore hardness	DIN 53505	Shore D	72 ± 2
Coefficient of linear expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	-
Linear shrinkage	internal	%	-

## Sales units (packages)

Units	Resin	SG 131 Comp. A	1,000 kg / 5,000 kg / 50,000 kg
	Hardener	PUR 11 Comp. B	1,000 kg / 5,000 kg / 50,000 kg

## Processing instructions

The fillers should be stirred into the single components A and B, so that they have nearly the same viscosity. After that both components can be very well mixed.

In case of small quantities and sufficient experience it is also possible to mix the unfilled components first and then to stir in the filler, without making the potlife too short for casting.

## In General

This is a Polyurethane system.

Material should be carefully stirred up/ shaken before use.

Filler content and sales units are on the separate mixing table noted.

## Storing

At room temperature (18 – 25°C) and closed original containers storage life is 6 months.

Partly used containers have always to be closed and the material has to be used up as soon as possible.

## Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany  
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . [info@ebalta.de](mailto:info@ebalta.de) . [www.ebalta.de](http://www.ebalta.de)