

|        |                   |
|--------|-------------------|
| Basis  | <b>ebaboard S</b> |
| Colour | red brown         |

## Application

- Master models
- Foundry patterns
- Architecture Models
- Coping models
- Inspection models
- Design Models
- Arts and Crafts

## Properties

- dense surface
- fine structure
- very well workable (contains no abrasive fillers)
- very good edge strength

## Working data

|                 |                     |             |
|-----------------|---------------------|-------------|
| <b>Product</b>  | <b>ebaboard S</b>   |             |
| Colour          | red brown           |             |
| Density at 20°C | g / cm <sup>3</sup> | 0,70 ± 0,02 |

## Physical data

| Properties                      | Inspect. requirem. | Unit                             | Value      |
|---------------------------------|--------------------|----------------------------------|------------|
| Flexural strength               | EN ISO 178         | MPa                              | 25,0 ± 3,0 |
| Flexural modulus                | EN ISO 178         | MPa                              | -          |
| Flexural strain at breakage     | EN ISO 178         | %                                | -          |
| Tensile strength                | EN ISO 527         | MPa                              | 15,0 ± 2,0 |
| Elongation at break             | ISO 37             | %                                | 4,0 ± 0,5  |
| Compressive strength            | EN ISO 604         | MPa                              | 24,0 ± 3,0 |
| Impact resistance (Charpy)      | EN ISO 179         | kJ/m <sup>2</sup>                | 6,0 ± 1,0  |
| Heat resistance (Martens)       | DIN 53458          | °C                               | 50 ± 2     |
| Heat resistance                 | -                  | °C                               | 75 ± 5     |
| Shore hardness                  | DIN 53505          | Shore D                          | 65 ± 3     |
| Coefficient of linear expansion | DIN 53752          | 10 <sup>-6</sup> K <sup>-1</sup> | ca. 55     |

## Sales units (packages)

|                   |                      |
|-------------------|----------------------|
| <b>ebaboard S</b> | 1500 x 500 x 25 mm•  |
|                   | 1500 x 500 x 50 mm•  |
|                   | 1500 x 500 x 75 mm•  |
|                   | 1500 x 500 x 100 mm• |
|                   | 1500 x 500 x 150 mm• |
|                   | 1500 x 500 x 200 mm  |

## Processing instructions

Advices for machining of board material.

- 
- Making even of milling support
- Roughing of geometry
- Removing of clamps, if possible over night
- Clamping
- Finishing
- 

The gluing of the board material is made with our „adhesive for board material“.

The glued parts are easily fixed by clamps or by weight.

Milling parameter are available.

## In General

**ebaboard** material is available in specified sizes. The surface is machined on all sides. **ebaboard** is a synthetic, post-cured board material on polyurethane base. It has an even structure and plane parallel machined surfaces.

Advantages:

- 
- Dense structure
- Good edge strength
- Low tension
- Good workability
- Low dust development when milling
- 
- Dimensional tolerance of 1-2 % is possible.
- 

"VP"-products are experimental products.

Regarding technical data slight modifications are possible.

## Safety measure

**ebaboard** material is a cured filled polyaddition product, no hazardous dusts when grinding.

Anyway the quantity of dusts coming from mechanical treatment of wood and metal 6 mg/m<sup>3</sup> (MAC-value)- must not be exceeded.

According to regulations for hazardous goods **ebaboard** products don't have to be marked during transport and storage.

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

## Waste Disposal

Small quantities can be disposed as domestic waste. For big quantities, contact your local authorities, please.

In case of further questions please do not hesitate to contact our department for product safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

**ebalta** Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany  
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . info@**ebalta**.de . www.**ebalta**.de