

Basis	good grinding, chemical resistant gelcoat
Resin	OH 35
Hardener	CH-1
Colour	black

Applications

- PU-foaming tools
- RIM foam tools
- Polyester press forms
- Prepreg tool
- Adhesive probes
- Vacuum forming tools

Properties

- chemical resistant
- polishable
- grinding possible
- dense surface
- heat resistant

Processing data

Product		Mixture OH 35 / CH-1	Resin OH 35	Hardener CH-1
Colour		black	black	yellow transparent
Mixing ratio	p. b. w.		100	16
Viscosity at 25°C	mPas	thixotrop	thixotrop	3500 ± 500
Density at 20°C	g / cm ³	1,60 ± 0,05	1,70 ± 0,05	1,08 ± 0,02
Pot life 200 g / 20°C	min.	20 - 30	-	-
Curing time at RT	hrs.	16 - 24	-	-
Post curing	Time in h/ Temperature in °C	10 - 12 / 60 - 80	-	-

Physical data

Properties	Inspect. requirem.	Unit	Value
Flexural strength	EN ISO 178	MPa	110 ± 10
Flexural modulus	EN ISO 178	MPa	5500 ± 500
Flexural strength at breakage	EN ISO 178	%	2,55 ± 0,25
Tensile strength	EN ISO 527	MPa	-
Tensile strength / test piece type 2	ISO 37	MPa	-
Elongation at break	ISO 37	%	-
Compressive strength	EN ISO 604	MPa	105 ± 10
Impact resistance (Charpy)	EN ISO 179	kJ/m ²	13,5 ± 3
Heat resistance (HDT)	DIN EN ISO 75 B	°C	98 ± 3
Glass transition temperature TG	methode DSC	°C	108
Shore hardness	DIN 53505	Shore D	88 ± 3
Coefficient of linear expansion	DIN 53752	10 ⁻⁶ K ⁻¹	ca. 55

Sales units (packages)

Packing size	A-Pack	OH 35 / CH-1	Resin 12 x 0,400 kg / Hardener 12 x 0,064 kg = 5,568 kg
Units	resin	OH 35	6,000 kg / 20,000 kg
	Hardener	CH-1	1,000 kg / 5,000 kg

Processing instructions

The temperature of material and processing should be between 18 and 25° C.

After each use the containers have to be closed again.

Porous mould surfaces should be sealed before (**ebalta** sealant).

For an optimum mould release we recommend a suitable release agent (e.g. T 1-1) which can be easily applied with a brush.

The mould should be treated 2 or 3 times with release agent and allowed to evaporate for approx. 20 min after every application.

Mixing ratio resin/hardener according to instructions!

Stirring rods etc. with residual resin can be easily cleaned with **ebalta** cleaning agent.

In General

ebalta OH 35 is a gelcoat which yields a very dense chemical resistant surface.

Due to its good grinding ability, damages can be amended very well without and any junctions.

Matt surfaces from wear-out effects can be silk-finish polished.

After curing at room temperature OH 35 isn't brittle, the moulds' edges are stable.

As coupling paste for the rear construction we recommend coupling paste KP 6/TGL.

Due to its thixotropic consistency the resin/hardener mixture can be easily applied without any bubbles with a short-haired brush in a layer of 1 mm. No sagging at edges, corners and vertical surfaces.

Apply two layers, the second one about 60 min after the first one.

We recommend postcuring for 10-12 hrs. at 60-80°C for long potlife and good heat resistance.

Storing

Storage at room temperature (18-25 °C) in closed original container 6 months.

Already opened containers should be closed immediately after use and should be used as soon as possible

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material. Please follow safety advices !

Waste Disposal

According to arrangement with local authorities cured material can be disposed as domestic or commercial waste.

Non-cured products are waste which is subject to inspection and has to be disposed accordingly.

In case of further questions please do not hesitate to contact our Department for Product Safety.

The instructions and recommendations are given in good faith and are based on long experience and careful tests. Since the conditions of use are beyond our control, and due to versatility of applications and working methods, we can't give any guarantee. All information are non-binding and are no guarantee for special characteristics or properties of the product. Despite information given from **ebalta** the customer has to make his own tests regarding applications and processing. If any special warranty is requested, written agreement on this subject is essential.

ebalta Kunststoff GmbH . Erlbacher Straße 100 . 91541 Rothenburg ob der Tauber / Germany
Tel.: +49 9861 7007-0 . Fax: +49 9861 7007-77 . info@ebalta.de . www.ebalta.de